




Normal size b		1 ×1.4	1.5 ×2.6	2 ×2.6	2 ×3.7	(2.5) ×3.7	3 ×3.7	3 ×5	3 ×6.5	4 ×5	4 ×6.5	4 ×7.5	5 ×6.5
b	min	0.975	1.475	1.975	1.975	2.475	2.975	2.975	2.975	3.97	3.97	3.97	4.97
	max=nominal size (h12)	1.4	2.6	2.6	3.7	3.7	3.7	5	6.5	5	6.5	7.5	6.5
k	min	1.3	2.5	2.5	3.58	3.58	3.58	4.88	6.35	4.88	6.35	7.35	6.35
	d1	4	7	7	10	10	10	13	16	13	16	19	16
L	≈	3.82	6.76	6.76	9.66	9.66	9.66	12.56	15.72	12.65	15.72	18.57	15.72
per 1000 units≈kg		0.031	0.153	0.204	0.414	0.518	0.622	1.1	1.8	1.47	2.4	3.27	3.01

Normal size b		5 ×7.5	5 ×9	6 ×7.5	6 ×9	6 ×10	6 ×11	8 ×9	8 ×11	8 ×13	10 ×11	10 ×13	10 ×16
b	min	4.97	4.97	5.97	5.97	5.97	5.97	7.964	7.964	7.964	9.964	9.964	9.964
	max=nominal size (h12)	7.5	9	7.5	9	(10)	11	9	11	13	11	13	16
k	min	7.35	8.85	7.35	8.85	9.85	10.82	8.85	10.82	12.82	10.82	12.82	15.82
	d1	19	22	19	22	25	28	22	28	32	28	32	45
L	≈	18.57	21.63	18.57	21.63	24.49	27.35	21.63	27.35	31.43	27.35	31.43	43.08
per 1000 units≈kg		4.09	5.73	4.91	6.88	8.64	10.6	9.17	14.1	19.3	17.6	24.1	39.9

①. Material

St 60 (steel of at least 60 kg / mm² tensile strength in finished condition), specify other materials when ordering.